

Material: LInNOTAM HiPERFORMANCE 1200

Stand 05/2020

Short description of material

LInNOTAM HiPERFORMANCE 1200 is produced in a pressureless static casting process through an anionic reaction. This method produces a high molecular and high crystalline material with relatively little stress. It has good wear resistance with a low coefficient of friction.

Application examples

- Gears & sprockets
- Cams
- Pump wheels and housings
- Mixing blades
- Boat propellers
- Idler wheels, guide rollers, sheaves.

Colours

natural

Mechanical values

ISO / EN / DIN

Dry

Humid

	ISO / EN / DIN	Dry	Humid	
Density	ISO 1183	1,03	--	g/cm ³
Yield stress	ISO 527	60	50	MPa
Elongation at break	ISO 527	55	120	%
Modulus of elasticity from tensile test	ISO 527	2200	1800	MPa
Modulus of elasticity from bending test	ISO 178	2400	--	MPa
Flexural Strength	ISO 178	90	--	MPa
Impact strength ¹⁾	ISO 179	without break	without break	KJ/m ²
Notched-bar Impact Strength	ISO 179	>15	--	KJ/m ²
Ball indentation hardness H358/30	ISO 2039-1	100	--	MPa
Creep rate stress at 1% Dehnung ²⁾	DIN EN ISO 899-1	>11	--	MPa
Sliding friction coefficient against steel (dry running) ³⁾	-	0,4	--	-
Sliding wear against steel (dry running) ³⁾	-	--	--	µm/km

Thermal values

	ISO / EN / DIN	Dry	Humid	
Melting temperature	ISO 3146	+190	--	°C
Thermal conductivity	DIN EN 12939	0,23	--	W/(K*m)
Specific thermal capacity	-	1,7	--	J/(g*K)
Coefficient of thermal expansion (linear) ⁴⁾	-	10-11	--	10 ⁻⁵ *K ⁻¹
Operating temperature range (long-term) ⁵⁾	-	-60 bis +110	--	°C
Operating temperature range (short-term) ⁵⁾	-	+150	--	°C
Fire behaviour	UL 94, IEC 60695	HB	--	-

Electrical values

	ISO / EN / DIN	Dry	Humid	
Dielectric constant ⁶⁾	IEC 60250	3,7	--	-
Dielectric loss factor ⁶⁾	IEC 60250	0,03	--	-
Specific volume resistance	IEC 60093	10 ¹⁵	--	Ω *cm
Surface resistance	IEC 60093	10 ¹³	--	Ω
Dielectric strength	IEC 60243	50	20	kV/mm
Creep current resistance	IEC 60112	CTI 600	--	-

Miscellaneous data

	ISO / EN / DIN	Dry	Humid	
Moisture absorption in normal climate until saturated	DIN EN ISO 62	0,9	--	%
Water absorption until saturated	DIN EN ISO 62	1,4	--	%

¹⁾ measured with a pendulum impact testing machine 0,1 DIN 51 222

²⁾ tension resulting in 1% total elongation after 1.000h

³⁾ against steel, hardened and ground

P = 0,05 Mpa; V = 0,6m/s; t = 60 °C near running surface

⁴⁾ For a temperature range of + 23 °C up to + 60 °C

⁵⁾ Experience values established with finished parts that are not under any stress in heated air, depending on the type and form of heat exposure, short-term = max. 1h, long-term=months

⁶⁾ at 10⁶ Hz

The content of this datasheet are meant to give an overview of the product's properties. It reflects our current knowledge and may not be complete. The values should be taken as guide values because they are very depend on surrounding conditions and machining methods. The values are in no way a legally binding assurance of the product's properties or its suitability for use in a specific application. All stated values are average values established from many individual tests. They are based on a temperature of 23°C and 50% RH. For specific applications, we recommend determining suitability by means of a trial.

Managing Director: Dr. Otto Lose

Phone: +49 2683 977-0

Fax: +49 2683 977-111

info@licharz.com

VAT-No.DE 260268077

Licharz GmbH
Industriepark Nord 13
53567 Buchholz
Germany

www.licharz.com